



Moisture Density Relationship

InTEC of San Antonio
12028 Radium
San Antonio, TX 78216
Phone: 210-525-9033

Client:
Pulte Homes of Texas, LP
1718 Dry Creek Way Suite 120
San Antonio, TX 78259

Project:
S212189
Corley Farms Unit 2
29.737543477901177, -98.71426779610178
Boerne, TX

SAMPLE DATA

Sample Number: 22199

Sample Date: 04/03/2023

Technician: Pereida, Gerald

Material Use: Street-Lime Subgrade


Sample Location: Windmill Breeze, STA 7+00

Material Description: Brown Clay

LAB DATA

Test Method: ASTM D1557 - Method C

Proctor Curve:



Maximum Dry Density (pcf): 93.2

Optimum Moisture (%): 27.6

Soil Classification: CH Clay - Lime Stabilized

Test Completed Date: 04/07/2023

Test Completed By: Efediyi, Eugene