



New Braunfels
2682 Wald Road
New Braunfels, TX 78132

04/04/2024

Concrete screenings-1037202

Procedure	Sieve/Test	Average	Unit	TXDOT Mn Snd Grading 1 (421-Fine)
	3/8" (9.5mm)	100.0	%	100-100
	#4 (4.75mm)	99.7	%	95-100
	#8 (2.36mm)	85.8	%	80-100
	#16 (1.18mm)	55.5	%	50-85
	#30 (.6mm)	30.6	%	25-65
	#40 (.425mm)	19.7	%	10-50
	#50 (.3mm)	12.8	%	10-35
	#100 (.15mm)	2.8	%	0-10
	#200 (75µm)	1.02	%	0-6

Name/Title

Robert E Latham / QC Manager